Birch Ply Laser



Metsä Wood Laser is interior bonded birch plywood. Laser plywood is available in two options: high quality uncoated, sanded plywood or plywood overlaid with a melamine film.

APPLICATIONS

Metsä Wood Laser is specially developed for laser cutting applications and is mostly used as die cutting plates in the packaging industry. Laser plywood is suitable also for other indoor uses and for applications requiring a colourless glue line with a protective, easy maintenance film surface. Laser is not suitable for outdoor use, because the base plywood bonding is not resistant to weather.

MAJOR ADVANTAGES

- Easy to machine with laser cutting devices
- · Colourless glueline
- Strong and rigid
- Excellent strength-to-weight ratio
- Dimensionally stable
- Easy to work with using conventional woodworking tools and fasteners
- Easy maintenance film surface
- Made of sustainable Nordic wood and PEFC (PEFC/02-31-381) certified





BASE PLYWOOD

The base plywood of Metsä Wood Laser is made of cross-bonded 1.4 mm thick birch veneers bonded with melamine urea formaldehyde adhesive.

OVERLAY

Metsä Wood Laser is available as sanded and uncoated product and as overlaid product with transparent film on both sides.

Metsä Wood Laser uncoated:

Both surfaces are sanded. The grade of surface veneer is BB quality. Uncoated Laser surface grades follow the classification presented in standard EN 635. The uncoated panel surface can be treated with standard paints, lacquers, varnishes and protection treatments applicable on wood products. Confirm the compatibility of a surface treatment from the supplier.

Metsä Wood Laser overlaid:

A smooth melamine film is hot-pressed on both panel surfaces to enhance surface durability.

SURFACE PROPERTIES

With colourless and transparent film, the colour of overlaid Metsä Wood Laser is similar to natural colour of the birch surface. The film surface and BB veneer grade is sufficient for technical applications, but not for visually demanding applications such as furniture.

The film surface is semi glossy, smooth, hard and slippery. It withstands abrasion, is moisture-resistant and can tolerate commonly used chemicals as well as diluted acids and alkalis. The Laser film surfaces are well suited for laser cutting.

EDGE SEALING

Metsä Wood Laser product edges are not painted or otherwise sealed.

PANEL SIZES

WIDTH (mm)						
LENGTH (mm)	2400	2440	2500	3000	3050	3300
1200*						
1220*						
1250*						
1500*						
1525*						
	1200* 1220* 1250* 1500*	LENGTH (mm) 2400 1200* 1220* 1250* 1500*	LENGTH (mm) 2400 2440 1200*	LENGTH (mm) 2400 2440 2500 1200* Image: square of the control of the contr	LENGTH (mm) 2400 2440 2500 3000 1200* Image: square of the control of the co	LENGTH (mm) 2400 2440 2500 3000 3050 1200* Image: square squa

^{*} The measurement indicates the orientation of the surface veneer grain.

Other sizes are available on request.

SIZE TOLERANCES

Measured in accordance with standard EN 324, the plywood size and squareness tolerances meet EN 315 requirements.

PANEL TOLERANCES

LENGTH / WIDTH	TOLERANCE
<1000 mm	± 1 mm
1 000 - 2 000 mm	± 2 mm
>2 000 mm	± 3 mm
Squareness	± 0.1 % or ±1 mm/m
Edge straightness	± 0.1 % or ±1 mm/m

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES

The thickness tolerances fulfil the requirements of standard EN 315 and are in part more stringent than the official requirements.

THICKNESSES, STRUCTURES AND THICKNESS TOLERANCES OF THE PANELS*

NOMINAL THICKNESS	NUMBER OF PLIES	THICKNESS	WEIGHT		
(mm)	(ant.)	min. (mm)	max. (mm)	kg/m²	
9	7	8.8	9.5	6.1	
12	9	11.5	12.5	8.2	
15	11	14.3	15.3	10.2	
18	13	17.1	18.1	12.2	
21	15	20.0	20.9	14.3	

^{*} Moisture content of the product affects its dimensions

BONDING CLASSES

Melamine urea formaldehyde adhesive is used in the production of interior bonded Metsä Wood Laser plywood. The melamine additive improves the moisture resistance of the glue line compared to that of a standard interior bonding. The gluing meets the requirements of the standard EN 314-2 / Class 1 (interior).

FORMALDEHYDE EMISSIONS

Determined according to EN 717-1, the formaldehyde emitted by Metsä Wood Laser falls far below the Class E1 requirement of \leq 0.100 ppm. The formaldehyde emission of Metsä Wood Laser uncoated is approximately 0.034 ppm and Metsä Wood Laser overlaid is approximately 0.023 ppm.



⁼ standard panel size

^{*} Average density of Metsä Wood birch plywood is 680 kg/m³ (at relative humidity of RH 65 %)

^{*} Customised tolerances are possible but must be agreed separately



APPROVALS AND DESIGN PROPERTIES

Metsä Wood Laser is CE and UKCA marked and the design properties are determined according to standard EN 13986. The design properties given in the Declaration of Performance (DoP) and in the UK Declaration of Conformity (UK DoC) are to be used for structural calculations with EN 1995 (Eurocode 5). The DoP documents can be downloaded from www.metsawood.com/dop and the UK DoC documents can be downloaded from www.metsawood.com/ukdoc.

Birch plywood production is managed according to the principles of standard ISO 9001. The quality and the constancy of performance of the product is controlled by regular third party inspections and audits.

MACHINING

Metsä Wood Laser plywood panels can be machined according to customer specification on request.

PACKAGING

Metsä Wood Laser panels are packed in moisture-resistant plastic

PACKING QUANTITIES

	NUMBER (OF PANELS	PER PALL	ET BY THI	CKNESS
PANEL SIZE (mm)	9	12	15	18	21
1500 / 1525 x 2400 - 3300 1200/1220/1250 x 3000-3300	65	50	40	35	30
1500 / 1525 x 1500-2135 1200/1220/1250 x 1200-2700	100	75	60	50	45

INSTALLATION INFORMATION AND STORAGE

As wood is a hygroscopic material, the relative humidity of surrounding conditions affects the moisture content of the plywood and therefore the dimensions and flatness of the panel.

Metsä Wood Laser panels should be conditioned properly to the moisture content of the end use application before final use.

FURTHER INFORMATION

- · Metsä Wood Laser Declaration of Performance (www.metsawood.com/dop)
- Metsä Wood Laser UK Declaration of Conformity (www.metsawood.com/ukdoc)

This leaflet is provided for information purposes only and no liability or responsibility of any kind is accepted by Metsä Wood or their representatives, although Metsä Wood has used reasonable efforts to verify the accuracy of any advice, recommendation or information. Metsä Wood reserves



